# Ancienne Belgique 7 Bordeaux

CLAY PAVERS



## COLOUR

An intense blend of dark red and bordeaux shades with nuances

## Product description

The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure. The shape is slightly irregular. Finally the bricks are processed until they have acquired a weathered shape, due to which the paver surface leaves a rustic, aged impression.

## TECHNICAL CHARACTERISTICS

The pavers are delivered with the following characteristics, in accordance with the CE and UKCA mark:

### CE label according to EN 1344 : 2013 / AC : 2015

| | |
|---|---|
| Manufacturing dimensions (L x W x H) | : *188x45x63 mm |
| Quantity / m² with a traditional joint | : ca. 111 |

## PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

| Aspect | Class | Mean | Individual |
|---|---|---|---|
| Water absorption NBN EN771 | Class W2 | max.5% | max.6% |
| Transverse breaking load NBN EN1344 | Class T4 | min 80 N/mm | min 64 N/mm |
| Abrasion resistance NBN EN1344 | Class A2 (+) | max.600 mm³ | max.800 mm³ |
| Frost resistance NBN EN1344 | Class FP100 | freeze/thaw resistant | freeze/thaw resistant |
| Size tolerance NBN EN1344 | NPD | NPD | NPD |
| Wet skid resistance NBN EN1344 | Class U3 | >55 | |
| Acid resistance NBN EN1344 | Class C | < 7% | |



ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel-bricksandpavers.com

# Ancienne Belgique 7 Bordeaux

CLAY PAVERS

**Productshot**





ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel-bricksandpavers.com