# DecimA Melange

CLAY PAVERS



## COLOUR
Black-brown-red with nuances

## Product description
The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure. The shape is slightly irregular. Finally the bricks are processed until they have acquired a weathered shape, due to which the paver surface leaves a rustic, aged impression.

## TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the Benor mark, the CE mark and UKCA mark.

### CE label according to EN 1344 : 2013 / AC : 2015

| | | |
|---|---|---|
| Manufacturing dimensions (L x W x H) | : *210x50x103 mm | on demand for projects > 2000 m² |
| Quantity / m² with a traditional joint | : ca. 91 | |
| Manufacturing dimensions (L x W x H) | : *210x67x103 mm | on demand for projects > 2000 m² |
| Quantity / m² with a traditional joint | : ca. 68 | |

## PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

| Aspect | Class | Mean | Individual |
|---|---|---|---|
| Water absorption NBN EN771 | Class W3 | max 3% | max 4% |
| Transverse breaking load NBN EN1344 | Class T4 | min 80 N/mm | min 64 N/mm |
| Abrasion resistance NBN EN1344 | Class A3 | max 450 mm³ | max 500 mm³ |
| Frost resistance NBN EN1344 | Class FP100 | freeze/thaw resistant | freeze/thaw resistant |
| Size tolerance NBN EN1344 | Class R1 | ± 0,4 √d | 0,6 √d (range) |
| Wet skid resistance NBN EN1344 | Class U3 | >55 | |
| Acid resistance NBN EN1344 | Klasse C | < 7% | < 7% |



**ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | 9700 OUDENAARDE | BELGIUM**
**T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel-bricksandpavers.com**

# DecimA Melange

CLAY PAVERS

**Productshot**

