SeptimA Anthracite

CLAY PAVERS



COLOUR
Anthracite

Product description
The bricks are formed individually in the sanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an sanded surface structure.

TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the Benor mark, the CE mark and UKCA mark.

CE label according to EN 1344 : 2013 / AC : 2015

Manufacturing dimensions (L x W x H)	: *217x52x70 mm
Quantity / m² with a traditional joint	: ca. 85

PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

Aspect	Class	Mean	Individual
Water absorption NBN EN771	W3	Max 3%	Max 4%
Transverse breaking load	T4	Min 80 N/mm	Min 64 N/mm
Abrasion resistance	A3	Max 450 mm³	Max 500 mm³
Frost resistance	FP100	freeze/thaw resistant	freeze/thaw resistant
Wet skid resistance	U3	>55	
Acid resistance	C	< 7%	
Size tolerance	R1	Max. ± 0,4 √d	Max. 0,6 √d

ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel-bricksandpavers.com

SeptimA Anthracite

CLAY PAVERS

Productshot

