# SeptimA Automne

CLAY PAVERS



## COLOUR
Brown-grey-red with nuances.

## Product description
The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure. The shape is slightly irregular. Finally the bricks are processed until they have acquired a weathered shape, due to which the paver surface leaves a rustic, aged impression.

## TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the Benor mark, the CE mark and UKCA mark.

### CE label according to EN 1344 : 2013 / AC : 2015

| | |
|---|---|
| Manufacturing dimensions (L x W x H) | : *217x52x70 mm |
| Quantity / $m^2$ with a traditional joint | : ca. 85 |

## PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

| Aspect | Class | Mean | Individual |
|---|---|---|---|
| Water absorption NBN EN771 | W3 | Max 3% | Max 4% |
| Transverse breaking load | T4 | Min 80 N/mm | Min 64 N/mm |
| Abrasion resistance | A3 | Max 450 $mm^3$ | Max 500 $mm^3$ |
| Frost resistance | FP100 | freeze/thaw resistant | freeze/thaw resistant |
| Wet skid resistance | U3 | >55 | |
| Acid resistance | C | < 7% | |
| Size tolerance* | NPD | NPD | NPD |



**ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | BE-9700 OUDENAARDE |**
**T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel-bricksandpavers.com**

# SeptimA Automne

CLAY PAVERS

**Productshot**

