

# SeptimA Carbon



## COLOUR

Black brown

## Product description

The bricks are formed individually in the unsanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an unsanded surface structure.

## TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the CE and UKCA mark.

### CE label according to EN 1344 : 2013 / AC : 2015

Manufacturing dimensions (L x W x H) : \*212x50x70 mm

Quantity / m<sup>2</sup> with a traditional joint : ca. 91

### PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

Aspect	Class	Mean	Individual
Water absorption NBN EN771	W3	Max 3%	Max 4%
Transverse breaking load	T4	Min 80 N/mm	Min 64 N/mm
Abrasion resistance	A3	Max 450 mm <sup>3</sup>	Max 500 mm <sup>3</sup>
Frost resistance	FP100	freeze/thaw resistant	freeze/thaw resistant
Wet skid resistance	U3	>55	
Acid resistance	C	< 7%	
Size tolerance	R1	Max. ± 0,4√d	Max. 0,6√d

# SeptimA Carbon

Productshot

