# SeptimA Gold Grey

CLAY PAVERS



## COLOUR

The colour is grey - yellow

## Product description

The bricks are formed individually in the sanded mould to a solid mass, pressed from clay of alluvial origin from an area located in the Scheldt basin and fired in a tunnel oven at a temperature of approximately 1180°C. On the narrow side the bricks have an sanded surface structure.

## TECHNICAL CHARACTERISTICS

The paving is laid in fired clay bricks of Belgian origin, quality class A, carrying the Benor mark, the CE mark and UKCA mark.

### CE label according to EN 1344 : 2013 / AC : 2015

| | |
|---|---|
| Manufacturing dimensions (L x W x H) | : *218x52x72 mm |
| Quantity / m² with a traditional joint | : ca. 85 |

## PHYSICAL AND MECHANICAL PROPERTIES ACCORDING TO EN 1344: 2013 / AC: 2015

| Aspect | Class | Mean | Individual |
|---|---|---|---|
| Water absorption NBN EN771 | W3 | Max 3% | Max 4% |
| Transverse breaking load | T4 | Min 80 N/mm | Min 64 N/mm |
| Abrasion resistance | A3 | Max 450 mm³ | Max 500 mm³ |
| Frost resistance | FP100 | freeze/thaw resistant | freeze/thaw resistant |
| Wet skid resistance | U3 | >55 | |
| Acid resistance | C | < 7% | |
| Size tolerance | R1 | Max. ± 0,4 √d | Max. 0,6 √d |



ORIGIN : VANDE MOORTEL NV | Scheldekant 5 | 9700 OUDENAARDE | BELGIUM
T +32 (0)55 33 55 66 | BTW BE 0432.038.790 | - info@vandemoortel-bricksandpavers.com

# SeptimA Gold Grey

CLAY PAVERS

**Productshot**

